

clear

The paper for uniform corporate communications

1809

What for	How	Why
<p>Brochures</p> <p>Annual Reports</p> <p>Stationery</p> <p>Posters</p> <p>Calendars</p> <p>Mailings</p> <p>Greeting cards</p> <p>Packaging</p>	<p>Offset printing</p> <p>Thermo-relief printing</p> <p>UV drying</p> <p>Oil-based and UV varnishes</p> <p>Dispersion varnishes</p> <p>Embossing</p> <p>Drilling and perforating</p> <p>Scoring, folding and die cutting</p> <p>Binding</p> <p>Inkjet- and Laserprint</p> <p>only Medley pure and clear</p>	<p>Four different papers in perfect white harmony</p> <p>Can be used separate or in combination</p> <p>Every surface is at the the top of its class</p> <p>Optimal printability</p>

What exactly

Characteristics	Unit			Standards
Grammage	g/m ²	100	200	EN ISO 536
Caliper	µm	85	150	EN 20534
Volume spec.	cm ³ /g	0,85	0,8	DIN 53105
Surface	pH	7	7	DIN 53124
Smoothness	Sec.	15	7	DIN 53107
Whiteness	%	91,5	91,5	DIN 53145-2
Transparency	%	73,5	65	DIN 53147



The mark of responsible forestry

Given values are targets and are subject to alterations.

reflex-paper.com