

**gloss**

### The paper for uniform corporate communications

1809

What for	How	Why
<b>Brochures</b> <b>Annual Reports</b> <b>Stationery</b> <b>Posters</b> <b>Calendars</b> <b>Mailings</b> <b>Greeting cards</b> <b>Packaging</b>	<b>Offset printing</b> <b>Thermo-relief printing</b> <b>UV drying</b> <b>Oil-based and UV varnishes</b> <b>Dispersion varnishes</b> <b>Embossing</b> <b>Drilling and perforating</b> <b>Scoring, folding and die cutting</b> <b>Binding</b> <b>Inkjet- and Laserprint</b> <b>only Medley pure and clear</b>	<b>Four different papers in perfect white harmony</b> <b>Can be used separate or in combination</b> <b>Every surface is at the the top of its class</b> <b>Optimal printability</b>

### What exactly

Characteristics	Unit								Standards
<b>Grammage</b>	<b>g/m<sup>2</sup></b>	<b>115</b>	<b>135</b>	<b>150</b>	<b>170</b>	<b>200</b>	<b>250</b>	<b>300</b>	<b>EN ISO 536</b>
<b>Caliper</b>	<b>µm</b>	<b>82</b>	<b>99</b>	<b>110</b>	<b>127</b>	<b>152</b>	<b>190</b>	<b>236</b>	<b>EN 20534</b>
<b>Volume spec.</b>	<b>cm<sup>3</sup>/g</b>	<b>0,71</b>	<b>0,74</b>	<b>0,74</b>	<b>0,75</b>	<b>0,76</b>	<b>0,76</b>	<b>0,79</b>	<b>DIN 53105</b>
<b>Surface</b>	<b>pH</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>&gt;8</b>	<b>DIN 53124</b>
<b>Roughness</b>	<b>µm (PPS)</b>	<b>0,7</b>	<b>0,7</b>	<b>0,7</b>	<b>0,7</b>	<b>0,7</b>	<b>0,7</b>	<b>0,7</b>	<b>DIN 8791-4</b>
<b>Optical Whiteness</b>	<b>%</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>100</b>	<b>DIN 53145-2</b>
<b>Gloss 75°</b>	<b>%</b>	<b>76</b>	<b>76</b>	<b>76</b>	<b>76</b>	<b>76</b>	<b>76</b>	<b>76</b>	<b>DIN 8254-1</b>
<b>Opacity</b>	<b>%</b>	<b>94</b>	<b>96</b>	<b>97</b>	<b>98</b>	<b>&gt;98,5</b>	<b>&gt;98,5</b>	<b>&gt;98,5</b>	<b>DIN 53416/ISO 2471</b>



The mark of responsible forestry

Given values are targets and are subject to alterations.

[reflex-paper.com](http://reflex-paper.com)