

velvet

The paper for uniform corporate communications

1809

What for	How	Why
<p>Brochures</p> <p>Annual Reports</p> <p>Stationery</p> <p>Posters</p> <p>Calendars</p> <p>Mailings</p> <p>Greeting cards</p> <p>Packaging</p>	<p>Offset printing</p> <p>Thermo-relief printing</p> <p>UV drying</p> <p>Oil-based and UV varnishes</p> <p>Dispersion varnishes</p> <p>Embossing</p> <p>Drilling and perforating</p> <p>Scoring, folding and die cutting</p> <p>Binding</p> <p>Inkjet- and Laserprint</p> <p>only Medley pure and clear</p>	<p>Four different papers in perfect white harmony</p> <p>Can be used separate or in combination</p> <p>Every surface is at the the top of its class</p> <p>Optimal printability</p>

What exactly

Characteristics	Unit								Standards
Grammage	g/m ²	115	135	150	170	200	250	300	EN ISO 536
Caliper	µm	91	110	123	143	173	214	263	EN 20534
Volume spec.	cm ³ /g	0,79	0,82	0,82	0,84	0,86	0,86	0,88	DIN 53105
Surface	pH	>8	>8	>8	>8	>8	>8	>8	DIN 53124
Roughness	µm (PPS)	1,3	1,3	1,3	1,3	1,3	1,5	1,5	DIN 8791-4
Optical Whiteness	%	100	100	100	100	100	100	100	DIN 53145-2
Gloss 75°	%	35	35	35	35	35	35	35	DIN 8254-1
Opacity	%	95	96,5	97,5	98,5	>98,5	>98,5	>98,5	DIN 53416/ISO 2471



The mark of responsible forestry

Given values are targets and are subject to alterations.

reflex-paper.com